

Guy Strand Datasheet

Guy strands secure many of the largest man-made structures, including power and telecommunications lines, railway signals, towers, and masts. Provide reliable support with Bekaert steel guy strand. Bekaert offers a variety of strengths and coatings and specifications including CSA-G12 for the Canada market.

Specifications [Imperial, per [CAN/CSA-G12 \(Latest Edition\)](#)]

Designated strand size (in)	Nominal strand wire diameter (in)	Nominal wire diameter (in*)	Nominal metallic cross-sectional area of the strand (in ²)	Number of wires	Approx. weight (lb/1000 ft)	Minimum breaking strength, lb				Minimum weight of zinc-coating (oz/ft ²)		
						Grade 110	Grade 160	Grade 180	Grade 220	Class A	Class B	Class C
3/16	0.195	0.065	0.0230	7	79.0	2,400	3,500	4,000	4,800	0.50	1.00	1.50
1/4	0.249	0.083	0.0380	7	129	3,900	5,700	6,400	7,900	0.60	1.20	1.80
9/32	0.285	0.095	0.0500	7	169	5,200	7,500	8,500	10,300	0.70	1.40	2.10
5/16	0.327	0.109	0.0650	7	223	6,800	9,900	11,100	13,600	0.80	1.60	2.40
3/8	0.36	0.12	0.0790	7	270	8,200	12,000	13,500	16,500	0.85	1.70	2.55
7/16	0.432	0.144	0.114	7	389	11,900	17,300	19,500	23,800	0.90	1.80	2.70
1/2	0.495	0.165	0.150	7	511	15,600	22,700	25,500	31,200	0.90	1.80	2.70
9/16	0.564	0.188	0.194	7	664	20,300	29,500	33,200	40,600	1.00	2.00	3.00
5/8	0.621	0.207	0.235	7	813	24,600	35,800	40,200	49,200	1.00	2.00	3.00
9/16	0.569	0.113/0.117	0.191	19	657	18,900	27,500	30,900	37,800	0.80	1.60	2.40
5/8	0.634	0.125/0.134	0.235	19	806	23,000	33,600	37,700	46,100	0.85	1.70	2.55
11/16	0.688	0.136/0.144	0.278	19	954	27,500	40,000	45,000	55,000	0.85/0.90	1.70/1.80	2.55/2.70
3/4	0.762	0.150/0.162	0.339	19	1,163	33,500	48,700	54,800	67,000	0.90	1.80	2.70
13/16	0.815	0.161/0.171	0.389	19	1,338	38,700	56,000	63,100	77,100	0.90	1.80	2.70
7/8	0.894	0.177/0.186	0.470	19	1,613	46,200	67,300	75,700	92,500	0.90	1.80	2.70
15/16	0.94	0.186/0.196	0.519	19	1,784	51,400	74,700	84,100	102,800	0.90/1.00	1.80/2.00	2.70/3.00

*In the construction of 19-wire strands, the smaller nominal wire size applies to the 6 and 12-wire layers and the larger nominal wire size applies to the center wire.

Specifications [SI Units, per CAN/CSA-G12 (Latest Edition)]

Designated strand size (mm)	Nominal strand wire diameter (mm)	Nominal wire diameter (mm*)	Nominal metallic cross-sectional area of the strand (mm ²)	Number of wires	Approx. weight (kg/1000m)	Minimum breaking strength, kN				Minimum weight of zinc-coating (g/m ²)		
						Grade 800	Grade 1100	Grade 1300	Grade 1500	Class A	Class B	Class C
5	5.10	1.70	15.9	7	130	12.0	16.5	19.5	22.5	150	300	450
6	6.30	2.10	24.2	7	190	18.0	25.0	30.0	34.5	150	300	450
7	7.20	2.40	31.7	7	250	24.0	33.0	39.0	45.0	180	360	540
8	8.40	2.80	43.1	7	340	33.0	45.0	53.0	61.5	244	488	730
9	9.00	3.00	49.5	7	390	37.5	52.0	61.0	70.5	244	488	730
10	10.8	3.60	71.3	7	560	54.0	74.5	88.0	102	259	519	780
12	12.6	4.20	97.0	7	760	74.0	101	120	138	275	549	825
14	14.4	2.80/3.20	119	19	930	85.5	118	139	161	244/259	488/519	730/780
16	16.2	3.20/3.40	154	19	1,210	110	152	180	208	259	519	780
18	18.2	3.60/3.80	195	19	1,530	140	193	228	263	259/275	519/549	780/825
20	20.2	4.00/4.20	240	19	1,890	173	238	281	324	275	549	825
22	22.2	4.40/4.60	290	19	2,280	209	287	340	392	275	549	825
24	24.2	4.80/5.00	345	19	2,710	249	342	404	466	305	610	915

*In the construction of 19-wire strands, the smaller nominal wire size applies to the 6 and 12-wire layers and the larger nominal wire size applies to the center wire.

ISO 14001
certified

ISO 9001
certified



Contact us

More
Information?

1395 South Marietta Parkway,
Building 500, Suite 100
Marietta, Georgia 30067, USA
770.514.2219

www.bekaert.com/power-utilities

Modifications reserved.

All details describe our products in general form only. For ordering and design only use official specifications and documents. Unless otherwise indicated, all trademarks mentioned in this brochure are registered trademarks of NV Bekaert SA or its subsidiaries. ©Bekaert 2022